

WORKWEAR FABRIC INFORMATION



FABRIC	Bravo	AVAILABLE WITH ORGANIC FAIRTRADE CERTIFIED COTTON
FINISH	Crease Resist	
PRODUCT CODE	0051 74	

FABRIC DESCRIPTION / CHARACTERISTICS	
BLEND (FIBRE CONTENT)	Polyester 40 %, Cotton 60 %
FINISHED WEIGHT	200 g/m ²
YARN COUNT	warp Nm 34 weft Nm 27
FINISHED CONSTRUCTION	warp 42 threads/cm weft 19 threads/cm
WEAVE	2x1 Z Twill
MINIMUM USABLE WIDTH	150 cm

PHYSICAL PERFORMANCE	PRE-TREATMENT		TEST METHOD	RESULTS	ETSA RATING
TENSILE STRENGTH	Warp Weft		ISO 13934-1	750 N 360 N	●●●
PILLING	ICI Pilling Box	36.000 Rev.	ISO 12945-1	4	N/A*
SHRINKAGE IN WASHING			5x @75 °C	± 2.5 %	●●●
Wash & Wear / Crease Recovery			3x ISO 15797	3	●●●

COLOUR PERFORMANCE			TEST METHOD	RESULTS	ETSA RATING
RUBBING DRY			ISO 105 X 12	4	N/A*
WASHING	Colour change		ISO 105 C06 E1S	4	N/A*
	Colour staining	PES	ISO 105 C06 E1S	3/4	N/A*
	Colour staining	COTTON	ISO 105 C06 E1S	3/4	N/A*
DRY CLEANING	Colour change		ISO 105 D 01	4	N/A*
PERSPIRATION	Colour change		ISO 105 E 04	4	N/A*
	Colour staining	PES	ISO 105 E 04	3/4	N/A*
	Colour staining	COTTON	ISO 105 E 04	3/4	N/A*
LIGHT FASTNESS			ISO 105 B 02	5	N/A*
NOTES	Colour performance results shown are average values. Dark and special colours may not meet figures quoted.				

OTHER PERFORMANCES	TEST METHOD	RESULT

NOTES	SPECIAL FEATURES
<p>Characteristics may vary within commercial tolerances.</p> <p>PRODUCT CARE – ALL FABRICS ARE ALSO TESTED TO KLOPMAN TEST METHODS.</p>	

CARE LABELLING	
<p>DOMESTIC WASH</p> <p>WHITE ONLY</p>	<p>INDUSTRIAL LAUNDRING</p> <p>SEE KLOPMAN LAUNDRING RECOMMENDATION.</p>

DATE 28/11/2012

www.klopman.com



This document is for information only. For a controlled document please contact our technical service.
N/A* Not available for this product.