

# WORKWEAR FABRIC INFORMATION



<b>FABRIC</b>	<b>Diva</b>
<b>FINISH</b>	<b>Crease Resist</b>
<b>PRODUCT CODE</b>	<b>0052 74</b>


FABRIC DESCRIPTION / CHARACTERISTICS	
BLEND (FIBRE CONTENT)	Polyester 40 %, Cotton 60 %
FINISHED WEIGHT	200 g/m <sup>2</sup>
YARN COUNT	warp Nm 51                      weft Nm 34
FINISHED CONSTRUCTION	warp 57 threads/cm              weft 27 threads/cm
WEAVE	Satin
MINIMUM USABLE WIDTH	150 cm

PHYSICAL PERFORMANCE	PRE-TREATMENT	TEST METHOD	RESULTS	ETSA RATING	
TENSILE STRENGTH	Warp Weft		ISO 13934-1 700 N 400 N	●●●	
PILLING	ICI Pilling Box	36.000 Rev.	ISO 12945-1	4	N/A*
SHRINKAGE IN WASHING		5x @75 °C	ISO 15797	± 2.5 %	●●●
Wash & Wear / Crease Recovery		3x ISO 15797	ISO 15487	3	●●●

COLOUR PERFORMANCE	TEST METHOD	RESULTS	ETSA RATING		
RUBBING DRY	ISO 105 X 12	4	N/A*		
WASHING	Colour change	ISO 105 C06 E1S	4	N/A*	
	Colour staining	PES	ISO 105 C06 E1S	3/4	N/A*
	Colour staining	COTTON	ISO 105 C06 E1S	3/4	N/A*
DRY CLEANING	Colour change	ISO 105 D 01	4	N/A*	
PERSPIRATION	Colour change	ISO 105 E 04	4	N/A*	
	Colour staining	PES	ISO 105 E 04	3/4	N/A*
	Colour staining	COTTON	ISO 105 E 04	3/4	N/A*
LIGHT FASTNESS	ISO 105 B 02	5	N/A*		
NOTES	Colour performance results shown are average values. Dark and special colours may not meet figures quoted.				

OTHER PERFORMANCES	TEST METHOD	RESULT

NOTES	SPECIAL FEATURES
<p>Characteristics may vary within commercial tolerances.</p> <p>PRODUCT CARE – ALL FABRICS ARE ALSO TESTED TO KLOPMAN TEST METHODS.</p>	 

CARE LABELLING	
<p>DOMESTIC WASH</p> 	<p>INDUSTRIAL LAUNDRING</p> <p>SEE KLOPMAN LAUNDRING RECOMMENDATION.</p> 